



Ministry of Higher Education and
Scientific Research
University of Baghdad
Institute of Laser for Postgraduate
Studies



Laser Cleaning of Low Carbon Steel Alloys AISI 1005 and AISI 1012

A Thesis

Submitted to the Institute of Laser for Postgraduate
Studies, University of Baghdad in Partial Fulfillment
of the Requirements for the Degree of Master of
Science in Laser / Mechanical Engineering

BY

Samir Noori Ali

2013 AD

1434 AH

ABSTRACT

Laser cleaning of plate metals are studied in the present work. Cleaning experiments are performed with a Q-switched Nd:YAG laser at wavelengths of 1064 and 532nm. Two plate metals were used in this work, Low Carbon Steel AISI 1012 of thickness 1mm and Low Carbon Steel AISI 1005 of thickness 0.65mm.

Three main parameters have been studied in the present work. These parameters are peak power P_p (5, 15, 30, 40 and 50 MW), pulse repetition rate P.R.R. (1, 2, 3, 4, 5 and 6Hz) and wavelength λ (106 and 532nm). Effects of these parameters have been studied using images taken by optical microscope and scanning electron microscope. Microstructural investigations have been studied. Also some mechanical tests have been carried out for the samples.

The optimum conditions for laser cleaning process were occurred at P_p of 40MW and P.R.R. of 4Hz with approximately same effect for both wavelengths. The depth of the removed layer of the contaminants can be controlled as a function of the peak power and the pulse repetition rate for the same wavelength for single laser pulse application without any effect on the base metal surface. This depth can be increased by increasing the peak power, but in this case some defects will occur which affecting the base metal properties. The experimental work has been supported by a computational work, where conditions have been simulated using MATLAB 2012B. There was a good agreement between the experimental and simulation results.



وزارة التعليم العالي والبحث العلمي
جامعة بغداد
معهد الليزر للدراسات العليا



التنظيم الليزري لسبائك الفولاذ منخفض الكاربون AISI 1005 و AISI 1012

رسالة مقدمة
إلى معهد الليزر للدراسات العليا / جامعة بغداد
كمجزء من متطلبات نيل شهادة ماجستير علوم في
الليزر / الهندسة الميكانيكية

من قبل
سامر نوري علي

الخلاصة

تم في هذا العمل البحثي دراسة تنظيف الصفائح المعدنية بالليزر. تجارب التنظيف تمت باستخدام ليزر النديميوم ياك النبضي بالنano ثانية عند الأطوال الموجية ١٠٦٤ و ٥٣٢ نانو متر. نوعين من العينات بشكل صفائح معدنية استعملت في هذا العمل هي عينات من الفولاذ منخفض الكاربون نوع AISI 1012 بسمك ٦٥، ٠ ملم، و عينات من الفولاذ المنخفض الكاربون نوع AISI 1005 بسمك ١ ملم، و عينات من الفولاذ المنخفض الكاربون نوع ٦٥، ٠ ملم.

هناك ثلاث متغيرات تم اختيارها في هذا العمل البحثي لغرض دراسة تأثيرها على عملية التنظيف الليزري هي قدرة الليزر العظمى بواقع (٥، ١٥، ٣٠، ٤٠، ٥٠ ميكواط) ومعدل التردد النبضي بواقع (١، ٢، ٣، ٤، ٥ و ٦ هيرتز) والطول الموجي لشعاع الليزر. تأثيرات هذه المتغيرات تم اختبارها عن طريق الصور، حيث تم التقاط هذه الصور بواسطة المجهر الضوئي وكذلك عن طريق صور المسح الإلكتروني الدقيق لدراسة البنية المجهرية لسطح العينات التي تم اختبارها ومعرفة مدى تأثير الليزر على هذه السطوح.

كذلك تم اختبار بعض الخصائص الميكانيكية للعينات موضوع البحث ، مثل دراسة الصلادة الدقيقة وكذلك اختبارات الخشونة السطحية قبل وبعد عملية التنظيف الليزري.

لُوحيَّ أنَّه يمكن السيطرة على عمق الطبقة المُزالة من الملوثات (طبقة الأكسيد والشحوم) بدون أي عيوب أو أثار سلبية على سطح العينات الأصلي عن طريق تطبيق عملية التنظيف الليزري بنبضة الليزر بدلاًلة تغيير قدرة الليزر العظمى ومعدل التردد النبضي لنفس الطول الموجي.

كما تم ملاحظة أن الظروف المثالية لعملية التنظيف الليزري للمعادن تمت عند مقدار قدرة عظمى (٤٠ ميكا واط) ومعدل تردد نبضي (٤ هيرتز) مع وجود فوارق طفيفة في قيم الفحوصات عند استخدام الطول الموجي الآخر للعمل، وذلك يعود إلى تقارب امتصاصية الطبقة الملوثة لكلا الطولين الموجيين ١٠٦٤ و ٥٣٢ نانومتر.

من خلال هذا العمل تبين أن عمق الإزالة يمكن زراعته ولكن هذه الزيادة ستكون على حساب التأثير على الخواص الأساسية لمعدن النموذج الأصلي.

بالإضافة إلى النتائج العملية، لقد تم إنجاز برنامج محاكاة الظروف التي استخدمت في الجانب العملي وتم الحصول على نتائج نظرية متوافقة بصورة جيدة ومتطابقة MATLAB 2012B باستخدام برنامج مع النتائج العملية.